

LINEAR TECHNOLOGY MATERIALS DECLARATION

ltc2955cts8-1#trpbf

(Engineering Calculation)

TSOT-23

(printed on: 2020-07-11 22:11:21)

TOTAL MASS (g) : 0.012265

| COMPONENT MATERIAL | VENDOR/ INDUSTRY NAMES | CONSTITUENT NAME | CAS NUMBER | CONSTITUENT MASS (g) | CONSTITUENT (PPM) OF MATERIAL | CONSTITUENT (PPM) OF TOTAL PKG. | | |
|--------------------------------|----------------------------------|--------------------------------|------------|----------------------|-------------------------------|---------------------------------|----------------|---------------------|
| Active Device | Linear Technology | Silicon (Si) | 7440-21-3 | 0.000544 | 1000000 | 44354.9726562 | | |
| Die Coat | Dow Corning | Silicone | 69430-27-9 | 0.000000 | 0 | 0 | | |
| Lead Frame | Cu | Copper (Cu) | 7440-50-8 | 0.004582 | 975000 | 373592.78125 | | |
| | | Iron (Fe) | 7439-89-6 | 0.000113 | 24000 | 9213.44140625 | | |
| | | Phosphorus (P) | 7723-14-0 | 0.000001 | 300 | 81.5348739624 | | |
| | | Zinc (Zn) | 7440-66-6 | 0.000003 | 700 | 244.604629517 | | |
| | | Nickel (Ni) | 7440-02-0 | 0.000000 | 0 | 0 | | |
| | | Silicon (Si) | 7440-21-3 | 0.000000 | 0 | 0 | | |
| | | Magnesium (Mg) | 7439-95-4 | 0.000000 | 0 | 0 | | |
| | | Tin (Sn) | 7440-31-5 | 0.000000 | 0 | 0 | | |
| Lead Frame Total: | | | | 0.004699 | 1000000 | 383132.40625 | | |
| Plating | PMI | Exter. Plating Pb | 7439-92-1 | 0.000000 | 0 | 0 | | |
| | | Exter. Plating Sn | 7440-31-5 | 0.000663 | 1000000 | 54032.34375 | | |
| | | External Plating Total: | | | | 0.000663 | 1000000 | 54032.34375 |
| | | Inter. Plating Ni | 7440-02-0 | 0.000000 | 0 | 0 | | |
| | | Inter. Plating Ag | 7440-22-4 | 0.000080 | 1000000 | 6522.79003906 | | |
| Internal Plating Total: | | | | 0.000080 | 1000000 | 6522.79003906 | | |
| Die Attach | ELECTRICALLY CONDUCTIVE ADHESIVE | Silver (Ag) | 7440-22-4 | 0.000169 | 800000 | 13779.3945312 | | |
| | | Tin (Sn) | 7440-31-5 | 0.000000 | 0 | 0 | | |
| | | Lead (Pb) | 7439-92-1 | 0.000000 | 0 | 0 | | |
| | | Silica (SiO2) | 60676-86-0 | 0.000000 | 0 | 0 | | |
| | | Indium (In) | 7440-74-6 | 0.000000 | 0 | 0 | | |
| | | Metal Oxide | | 0.000000 | 0 | 0 | | |
| | | Antimony (Sb) | 7440-36-0 | 0.000000 | 0 | 0 | | |
| | | Resin (EP) | | 0.000042 | 200000 | 3424.46484375 | | |
| Die Attach Total: | | | | 0.000211 | 1000000 | 17203.859375 | | |
| Encapsulation | MULTI-AROMATIC RESIN Br/Sb FREE | Resin (EP) | | 0.000777 | 130000 | 63352.6015625 | | |
| | | Bromine (Br) | 40039-93-8 | 0.000000 | 0 | 0 | | |
| | | Silica (SiO2) | 60676-86-0 | 0.004963 | 830000 | 404657.5625 | | |
| | | Antimony Trioxide (Sb2O3) | 1309-64-4 | 0.000000 | 0 | 0 | | |
| | | Metal Hydroxide | | 0.000209 | 35000 | 17040.7890625 | | |
| | | Carbon Black (C) | 1333-86-4 | 0.000030 | 5000 | 2446.04614258 | | |
| | | Encapsulation Total: | | | | 0.005979 | 1000000 | 487497.03125 |
| Bond Wire Estimated | AFW/TANAKA/ Kn | Gold (Au) | 7440-57-5 | 0.000089 | 1000000 | 7256.60400391 | | |
| | | | | | TOTAL MASS (g) : | 0.012265 | | |